



250HR

High Performance Laminate and Prepreg Materials with High Thermal Reliability

250HR laminate and prepreg materials are a high-performance 150°C glass transition temperature (Tg) FR-4 system for multilayer Printed Wiring Board (PWB) applications where maximum thermal performance and reliability are required.

The 250HR system is manufactured with a unique high-performance, multifunctional epoxy resin, reinforced with electrical grade (E-glass) glass fabric. This system provides improved thermal performance and low expansion rates in comparison to traditional FR-4 while retaining FR-4 processability. In addition to this superior thermal performance, the mechanical, chemical and moisture resistance properties all equal or exceed the performance of traditional FR-4 materials.

The 250HR system is also laser fluorescing and UV blocking for maximum compatibility with Automated Optical Inspection (AOI) systems, optical positioning systems and photoimagable solder mask imaging.

Product Attributes

High Thermal Reliability

Typical Market Applications

Aerospace & Defense

Computing, Storage & Peripherals

Networking & Communication Systems

Automotive & Transportation

ORDERING INFORMATION:

Contact your local sales representative or visit www.isola-group.com for further information.

Isola Group
3100 West Ray Road
Suite 301
Chandler, AZ 85226
Phone: 480-893-6527
Fax: 480-893-1409
info@isola-group.com

Isola Asia Pacific (Hong Kong) Ltd.
Unit 3512 - 3522, 35/F
No. 1 Hung To Road, Kwun Tong,
Kowloon, Hong Kong
Phone: 852-2418-1318
Fax: 852-2418-1533
info.hkg@isola-group.com

Isola GmbH
Isola Strasse 2
D-52348 Düren, Germany
Phone: 49-2421-8080
Fax: 49-2421-808164
info-dur@isola-group.com

Tg 150°C

Td 325°C

Dk 4.00

Df 0.020

IPC-4101 - /21 /24 /97 /101

UL - File Number E41625

Last Updated Mar 16, 2017

Product Features

- Industry Recognition
 - UL File Number: E41625
 - Qualified to UL's MCIL Program
 - RoHS Compliant
- Processing Advantages
 - FR-4 process compatible
 - UV blocking and AOI fluorescence

Product Availability

- Standard Material Offering: Laminate
 - 2 to 93 mil (0.05 to 2.4 mm)
 - Available in full size sheet or panel form
- Copper Foil Type
 - HTE Grade 3
 - RTF (Reverse Treat Foil)
- Copper Weight
 - ½ to 2 oz (18 to 70 µm) available
 - Heavier copper available
 - Thinner copper foil available
- Standard Material Offering: Prepreg
 - Roll or panel form
- Glass Fabric Availability
 - E-glass
 - Square weave glass

Property	Typical Value	Units		Test Method
		Metric (English)		IPC-TM-650 (or as noted)
Test data generated from rigid laminate		50	%	2.3.16.2
Glass Transition Temperature (Tg) by DSC		150	°C	2.4.25C
Decomposition Temperature (Td) by TGA @ 5% weight loss		325	°C	2.4.24.6
Time to Delaminate by TMA (Copper removed)	A. T260 B. T288	30 >5	Minutes	2.4.24.1
Z-Axis CTE	A. Pre-Tg B. Post-Tg C. 50 to 260°C, (Total Expansion)	65 250 3.4	ppm/°C ppm/°C %	2.4.24C
X/Y-Axis CTE	Pre-Tg	13	ppm/°C	2.4.24C
Thermal Conductivity		0.45	W/mK	ASTM E1952
Thermal Stress 10 sec @ 288°C (550.4°F)	A. Unetched B. Etched	Pass	Pass Visual	2.4.13.1
Dk, Permittivity	A. @ 2 GHz B. @ 5 GHz	4.00 3.90	—	Bereskin Stripline
Df, Loss Tangent	@ 2 GHz	0.020	—	Bereskin Stripline
Dk, Permittivity	@ 5 GHz	0.022	—	Bereskin Stripline
Volume Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 2.4×10^8 2.3×10^8	MΩ-cm	2.5.17.1
Surface Resistivity	A. C-96/35/90 B. After moisture resistance C. At elevated temperature	— 2.6×10^8 2.8×10^8	MΩ	2.5.17.1
Dielectric Breakdown		>50	kV	2.5.6B
Arc Resistance		105	Seconds	2.5.1B
Electric Strength (Laminate & laminated prepreg)		48 (1200)	kV/mm (V/mil)	2.5.6.2A
Comparative Tracking Index (CTI)		3 (175-249)	Class (Volts)	UL 746A ASTM D3638
Peel Strength	A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil]	1.05 (6.0)	N/mm (lb/inch)	2.4.8C
	B. Standard profile copper	1.58 (9.0)		2.4.8.2A
	1. After thermal stress	1.23 (7.0)		2.4.8.3
	2. At 125°C (257°F)	1.58 (9.0)		2.4.8.3
Flexural Strength	A. Length direction	86,000		2.4.4B
	B. Cross direction	84,100		
Tensile Strength	A. Length direction	56,810		ASTM D3039
	B. Cross direction	43,745		
Moisture Absorption		0.3	%	2.6.2.1A
Flammability (Laminate & laminated prepreg)		V-0	Rating	UL 94
Max Operating Temperature		130	°C	UL 796

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

isola.keostaging.com/products/printed-circuit-materials/market-segment/automotive/

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. 250HR is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.

