



PRODUCTS

Welcome to Our website.
We provide the best service, hope you will like.
Our goal is to provide exceptional service
and support to our customers.

INNOVATION • TEAMWORK • EXCELLENCE • QUALITY

Welcome to Our website.
We provide the best service, hope you will like.

IT-588BS/IT-588TC

Multifunctional Epoxy Resin and Laminate and Prepreg

IT-588 is a medium Tg (>135 °C by DSC) multifunctional filled epoxy with high thermal reliability and CAF resistance. It's suitable for consumer applications and also can pass 260 °C Lead free assembly.

Key Features =====

Advanced Resin Technology

Industrial standard material with medium Tg (135 °C by DSC) multifunctional epoxy resin and excellent thermal reliability.

Lead-Free Assembly Compatible

RoHS compliant and suitable for high thermal reliability needs, and Lead free assemblies with a maximum reflow temperature of 260 °C.

Friendly Processing and CAF Resistance

Friendly to PCB process that users can easily handle the process by current equipment and chemical.

CAF Resistance

Excellent thermal reliability and CAF resistance providing long-term reliability for industrial boards and automobile application.

Available in Variety of Constructions

Available in a various of constructions, copper weights and glass styles, including standard(HTE), RTF and VLP copper foil.

Applications

PC and Notebook

Memory Module

Game Player

Multilayer PCB

Servers and Networking

Telecommunications

Industrial Approval

UL 94 V-0

IPC-4101C Spec / 101

RoHS Compliant

ITEQ Laminate/ Prepreg : IT-588TC / IT-588BS

IPC-4101C Spec / 101

LAMINATE (IT-588TC)

Property	Thickness < 0.50 mm [0.0197 in]		Thickness ≥ 0.50 mm [0.0197 in]		Units	Test Method
	Typical Value	Spec	Typical Value	Spec	Metric (English)	IPC-TM-650 (or as noted)
Peel Strength, minimum A. Low profile copper foil and very low profile copper foil - all copper weights > 17µm [0.669 mil] B. Standard profile copper foil 1. After Thermal Stress 2. At 125°C [257 F] 3. After Process Solutions	0.88 (5.0)	0.70 (4.00)	0.88 (5.0)	0.70 (4.00)	N/mm (lb/inch)	2.4.8 2.4.8.2 2.4.8.3
Volume Resistivity, minimum A. C-96/35/90 B. After moisture resistance C. At elevated temperature E-24/125	3.0x10 ¹⁰ -- 5.0x10 ¹⁰	10 ⁶ -- 10 ³	-- 5.0x10 ¹⁰ 1.0x10 ¹⁰	-- 10 ⁴ 10 ³	MΩ-cm	2.5.17.1
Surface Resistivity, minimum A. C-96/35/90 B. After moisture resistance C. At elevated temperature E-24/125	1.0x10 ¹⁰ -- 5.0x10 ¹⁰	10 ⁴ -- 10 ³	-- 1.0x10 ¹⁰ 3.0x10 ¹⁰	-- 10 ⁴ 10 ³	MΩ	2.5.17.1
Moisture Absorption, maximum	--	--	0.08	0.5	%	2.6.2.1
Dielectric Breakdown, minimum	--	--	60	40	kV	2.5.6
Permittivity (Dk, 50% resin content) (Laminate & Laminated Prepreg) A. 1MHz B. 1GHz C. 2GHz D. 5GHz E. 10GHz	4.7 4.6 4.6 4.5 4.4	5.4	4.7 4.6 4.6 4.5 4.5	5.4	--	2.5.5.9 2.5.5.13
Loss Tangent (Df, 50% resin content) (Laminate & Laminated Prepreg) A. 1MHz B. 1GHz C. 2GHz D. 5GHz E. 10GHz	0.017 0.018 0.018 0.019 0.019	0.035	0.017 0.018 0.018 0.019 0.019	0.035	--	2.5.5.9 2.5.5.13
Flexural Strength, minimum A. Length direction B. Cross direction	-- -- --	-- -- --	540-570 (78,300-82,650) 450-480 (65,250-69,600)	415 (60,190) 345 (50,140)	N/mm ² (lb/in ²)	2.4.4
Arc Resistance, minimum	120	60	120	60	s	2.5.1
Thermal Stress 10 s at 288°C [550.4F], minimum A. Unetched B. Etched	Pass Pass	Pass Visual Pass Visual	Pass Pass	Pass Visual Pass Visual	Rating	2.4.13.1
Electric Strength, minimum (Laminate & Laminated Prepreg)	45	30	--	--	kV/mm	2.5.6.2
Flammability, (Laminate & Laminated Prepreg)	V-0	V-0	V-0	V-0	Rating	UL94
Glass Transition Temperature(DSC)	137	135 minimum	137	135 minimum	°C	2.4.25
Decomposition Temperature	--	--	345	340 minimum	°C	2.4.24.6 (5% wt loss)
X/Y Axis CTE (40°C to 125°C)	--	--	11-14	--	ppm/°C	2.4.24
Z-Axis CTE A. Alpha 1 B. Alpha 2 C. 50 to 260 Degrees C	-- -- --	-- -- --	50 260 3.8	60 maximum 300 maximum 4.0 maximum	ppm/°C ppm/°C %	2.4.24
Thermal Resistance A. T260 B. T288	-- --	-- --	>60 >15	30 minimum 5 minimum	Minutes Minutes	2.4.24.1
CAF Resistance	--	--	Pass	AABUS	Pass/Fail	2.6.25

The above data and fabrication guide provide designers and PCB shop for their reference. We believe that these information are accurate, however, the data may vary depend on the test methods and specification used. The actual sales of the product should be according to specification in the agreement between ITEQ and its customer. ITEQ reserves the right to revise its data at any time without notice and maintain the best information available to users.