

DuPont™ Pyralux® LF Copper-Clad Laminates

flexible composites

Technical Information

Description

DuPont™ Pyralux® copper-clad laminated composites are constructed of DuPont™ Kapton® polyimide film with copper foil on one or both sides, bonded together with a proprietary C-staged modified acrylic adhesive. All copper-clad laminates are available with rolled, annealed copper or electro-deposited copper. In addition, both types are available with double-treated copper (nodules of electro-deposited copper on both sides of the copper foil). Double-treated copper, if used, eliminates surface preparation steps prior to resist or coverlay lamination.

Pyralux® laminated composites are typically used to produce high reliability, high density circuitry of flexible, rigid-flex, and all-flexible multilayer constructions. Techniques commonly used in the manufacture of flexible circuits can be used to process Pyralux® composites.

Construction

Copper-clad laminates are available in a variety of film thicknesses and copper weights. **Tables 1** and **2** list typical constructions. The product code must be used when ordering copper-clad laminates from DuPont.

Packaging

Pyralux® copper-clad laminates are supplied in 24-inch (610 mm) by 36-inch (914 mm) sheets. There is a minimum of four sheets and a maximum of 25 sheets per pack.

Typical Data

Each manufactured lot, except the laminate constructions noted in **Tables 1** and **2**, is certified to IPC specifications and tested according to IPC Test Method TM-650. See **Table 3**.

Table 1
Single-Sided Copper-Clad Product Codes

Product Code*	Copper	Adhesive	Kapton®	IPC
	oz/ft² (g/m²)	Mil (µm)	Mil (µm)	Cert.¹
LF9110R	1 (305)	1 (25)	1 (25)	Yes
LF9120R	1 (305)	1 (25)	2 (51)	Yes
LF9130R	1 (305)	1 (25)	3 (76)	Yes
LF9150R	1 (305)	1 (25)	5 (127)	Yes
LF9210R	2 (610)	1 (25)	1 (25)	Yes
LF9220R	2 (610)	1 (25)	2 (51)	Yes
LF7012R	1/2 (153)	1/2 (13)	1/2 (13)	No
LF7002R	1 (305)	1/2 (13)	1/2 (13)	No
LF7062R	1/2 (153)	1/2 (13)	1 (25)	No
LF7011R	1 (305)	1/2 (13)	1 (25)	Yes
LF7008R	2 (610)	1/2 (13)	1 (25)	Yes
LF7092R	1 (305)	1/2 (13)	2 (51)	Yes
LF7004R	1/2 (153)	1 (25)	1/2 (13)	No
LF7037R	1 (305)	1 (25)	1/2 (13)	No
LF7038R	2 (610)	1 (25)	1/2 (13)	No
LF8510R	1/2 (153)	1 (25)	1 (25)	Yes
LF7031R	3/4 (229)	1 (25)	1 (25)	Yes
LF8520R	1/2 (153)	1 (25)	2 (51)	Yes
LF7019R	3/4 (229)	1 (25)	2 (51)	Yes
LF7097R	1 (305)	2 (51)	1 (25)	Yes

*Add "R" to the end of the code to specify rolled-annealed copper (e.g., LF9210R). Add "E" to the end of the code to specify electro-deposited copper (e.g., LF9210E). If rolled annealed double-treated copper is specified, add the letter "D" to the end of the product code (e.g., LF9210D).
¹Certified to IPC-4204/1: "Flexible Metal-Clad Dielectrics for use in Fabrication of Flexible Printed Wiring."

A Certificate of Analysis is available with every batch. Complete material and manufacturing records for each lot, with samples of finished laminate, are retained for reference purpose. The roll labels contain the lot number, DuPont order number, customer order number, IPC specification, customer specification, and customer part number; save these labels for reference in case of inquiries.



The miracles of science™

Table 2
Double-Sided Copper-Clad Product Codes

Product Code*	Copper	Adhesive	Kapton®	IPC
	oz/ft ² (g/m ²)	Mil (µm)	Mil (µm)	Cert. ¹
LF9111R	1 (305)	1 (25)	1 (25)	Yes
LF9121R	1 (305)	1 (25)	2 (51)	Yes
LF9131R	1 (305)	1 (25)	3 (76)	Yes
LF9151R	1 (305)	1 (25)	5 (127)	Yes
LF9212R	2 (610)	1 (25)	1 (25)	Yes
LF9222R	2 (610)	1 (25)	2 (51)	Yes
LF7022R	1/2 (153)	1/2 (13)	1/2 (13)	No
LF7014R	1/2 (153)	1/2 (13)	1 (25)	No
LF7010R	1 (305)	1/2 (13)	1 (25)	Yes
LF7041R	2 (610)	1/2 (13)	1 (25)	Yes
LF7091R	1/2 (153)	1/2 (13)	2 (51)	Yes
LF7093R	1 (305)	1/2 (13)	2 (51)	Yes
LF7058R	2 (610)	1/2 (13)	2 (51)	Yes
LF7003R	2 (610)	1/2 (13)	3 (76)	No
LF7017R	1/2 (153)	1 (25)	1/2 (13)	No
LF7039R	1 (305)	1 (25)	1/2 (13)	No
LF7040R	2 (610)	1 (25)	1/2 (13)	No
LF8515R	1/2 (153)	1 (25)	1 (25)	Yes
LF8525R	1/2 (153)	1 (25)	2 (51)	Yes
LF7090R	2 (610)	2 (51)	2 (51)	Yes
LF7071R	1 (305)	1/2 (13)	1/2 (13)	Yes

*Add "R" to the end of the code to specify rolled-annealed copper (e.g., LF9210R). Add "E" to the end of the code to specify electro-deposited copper (e.g., LF9210E). If rolled annealed double-treated copper is specified, add the letter "D" to the end of the product code (e.g., LF9210D).
¹Certified to IPC-4204/1: "Flexible Metal-Clad Dielectrics for use in Fabrication of Flexible Printed Wiring."

Processing

Laminating conditions for Pyralux® flexible composites are typically in the following ranges:

Part Temperature: 182–199°C (360–390°F)
 Pressure: 14–28 kg/cm² (200-400 psi)
 Time: 1–2 hours, at temperature

For further processing information contact your DuPont representative to receive a Pyralux® Technical Manual.

Storage Conditions and Warranty

Pyralux® LF flexible laminates should be stored in the original packaging at temperatures of 4–29°C (40–85°F) and below 70% humidity. The product should not be frozen and should be kept dry, clean and well protected. Subject to compliance with the foregoing handling and storage recommendations, the DuPont warranty, as provided in the DuPont Standard Conditions of Sale, shall remain in effect for a period of two years following the date of shipment.

Table 3
Copper-Clad Laminate Properties vs IPC Specifications

Property	IPC Spec	Typical Clad Value
Peel Strength, min., lb/in (kg/cm) As received As solder	8 (1.4) 7 (1.3)	10 (1.8) 9 (1.6)
Dimensional Stability, max., percent	0.15	0.10
Dielectric Constant, max. (at 1 MHz)	4.0	3.6
Dissipation Factor, max. (at 1 MHz)	0.03	0.02
Volume Resistivity, min., megohm-cm (ambient)	10 ⁷	10 ⁹
Surface Resistivity, min., megohm-cm (ambient)	10 ⁶	10 ⁸

* The values in Table 3 represent a typical 1 oz copper foil, 1 mil adhesive and 1 mil Kapton® construction.

Safe Handling

Pyralux® copper-clad laminated composites are supplied in sheets and are fully cured (C-staged).

DuPont is not aware of anyone developing contact dermatitis, or suffering any other medical discomforts, when using Pyralux® products. The uncured acrylic monomers in the bond ply adhesive may impart a mild odor. However, these products have been extensively tested under operating conditions (drilling and lamination conditions) and found to liberate measurable volatiles only well below¹ accepted safe limits (e.g., PEL).

To eliminate contact between the skin and exposed adhesive after etching, wear lint-free gloves or fingerpads. Anyone handling Pyralux® should wash their hands with soap before eating, smoking, or using restroom facilities. Gloves and fingerpads should be changed daily, and wash other protective clothing frequently.

Adequate ventilation and exhaust is recommended in press rooms to prevent the buildup of potentially harmful vapors, to remove disagreeable odors, and to dissipate heat. Drill rooms should be furnished with standard equipment recommended by drill vendors and required by OSHA standards.

For further information on safe handling, refer to DuPont publication H-46873, "Pyralux® LF and FR Safe Handling;" and refer to "Industrial Ventilation," 18th Edition or latest available from the American Conference of Governmental Industrial Hygienists, 6500 Glenway, Building D-5, Cincinnati, OH 45211.

¹Values for all materials monitored were well below 10% of their accepted limits (PEL or TLV). In only one case, did the concentration reach approximately 40% of its limit. This was an oven used to dry the uncured acrylic material. This oven drying is not normally used in the process and during the exposure the oven was unventilated. Adequate ventilation is normally recommended for any heating process.

For more information on DuPont™ Pyralux® flexible circuit materials, please contact your local representative, or visit our website:

Americas

DuPont Electronic Technologies
14 T. W. Alexander Drive
Research Triangle Park, NC 27709
Tel: 800-243-2143

Europe, Middle East & Africa

DuPont de Nemours (Luxembourg) s.à r.l.
Rue Général Patton, Contern
L-2984 Luxembourg
Tel: +352 3666 5935

Japan

DuPont KK
Sanno Park Tower
11-1, Nagata-cho 2-chome
Chiyoda-ku, Tokyo 100-6111
Tel: 81-3-5521-8660

Taiwan

DuPont Taiwan Hsinchu Branch.
#2, Li-Hsin 4th Rd., Hsinchu Science Park,
Hsinchu 30078, Taiwan
Tel: 886-3-5793654

India

E.I. DuPont India Limited
1001-1012 "Meadows", 10th Floor
Sahar Plaza Complex
Andheri-Kurla Road, Andheri
(East)
Mumbai 400 059, India
Tel: 91-22-6751-5000

DID: 91-22-6751-5038
Fax : 91-22-67101937

China

DuPont China Holding Co., Ltd.
Shanghai Branch
Bldg. 11, 399 Keyuan Road
Zhangjiang Hi-Tech Park
Pudong New District
Shanghai 201203, China
Tel: 86-21-38622720

Korea

DuPont Korea Inc.
4/5 Floor, Asia Tower
#726, Yeoksam-dong, Kangnam-ku,
Seoul
135-082 Korea
Tel: 82-2-2222-5224

Singapore

DuPont Singapore Pte, Ltd.
1 HarbourFront Place #11-01
HarbourFront Tower One
Singapore 098633
Tel: 65-6586-3091

pyralux.dupont.com

Copyright ©2012 DuPont or its affiliates. All rights reserved. The DuPont Oval, DuPont™, The miracles of science™, Pyralux® and Kapton® are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

TCR® is a registered trademark of Ticer Technologies.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF DUPONT.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102.

This information is based on data believed to be reliable, but DuPont makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed herein falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. Because DuPont cannot anticipate or control the many different conditions under which this information and/or product may be used, it does not guarantee the usefulness of the information or the suitability of its products in any given application. Users should conduct their own tests to determine the appropriateness of the product for their particular purposes.

This information may be subject to revision as new knowledge and experience become available. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patent.

H-73244-5 06/12



The miracles of science™